

5 Claims

What is claimed is:

1. A method for manufacturing a slider comprising the steps of:
 - applying a liquid solution of polyvinyl alcohol to the slider;
 - 10 drying the slider to remove solvent from the liquid solution leaving a polyvinyl alcohol film on the slider;
 - binding the slider in a matrix material with the polyvinyl alcohol film being in contact with the matrix material;
 - performing a selected process on the slider while the slider is held in the
 - 15 matrix material; and
 - removing the matrix material and the alcohol film from the slider by a method including use of a first solvent to soften the polyvinyl alcohol film.
2. The method of claim 1 wherein the matrix material and the polyvinyl alcohol
- 20 film are resistant to a second solvent and the selected process forms an air-bearing pattern and includes use of the second solvent.
3. The method of claim 1 wherein the polyvinyl alcohol has a percentage hydrolysis of about 95% or greater.
- 25
4. The method of claim 1 wherein the polyvinyl alcohol has a percentage hydrolysis of about 99% or greater.
5. The method of claim 1 wherein the matrix material is an epoxy, acrylate,
- 30 polyimide or silsesquioxane.
6. The method of claim 1 wherein the polyvinyl alcohol has a molecular weight of about 124k to about 180k daltons.
- 35
7. The method of claim 1 wherein the liquid solution of polyvinyl alcohol comprises isopropanol.

- 5
8. The method of claim 2 wherein the liquid solution of polyvinyl alcohol comprises isopropanol and water.
9. The method of claim 1 wherein the step of drying the slider further comprises
- 10 baking at a first temperature followed by baking at a second temperature where the second temperature is higher than the first temperature.
10. The method of claim 1 wherein the first solvent comprises hot n-methyl-2-pyrrolidone.
- 15
11. The method of claim 1 wherein the first solvent comprises dimethylpropyl urea.
12. The method of claim 1 wherein the first solvent comprises boiling water.
- 20
13. A method for manufacturing sliders for use in disk drives comprising the steps of:
- attaching the sliders to a support surface;
- applying polyvinyl alcohol in a solution comprising water to the sliders;
- 25 drying the sliders leaving a coating of polyvinyl alcohol on the sliders;
- binding the sliders in a solid material which is resistant to a first solvent and to processing conditions of a selected photolithographic process;
- using the selected photolithographic process to form air-bearing features on a surface of the sliders; and
- 30 applying a second solvent to soften the coating of polyvinyl alcohol to aid in removing the solid material from the sliders.
14. The method of claim 13 wherein the polyvinyl alcohol has a percentage hydrolysis of about 95% or greater.
- 35

- 5 15. The method of claim 13 wherein the matrix material is an epoxy, acrylate,
polyimide or silsesquioxane.
16. The method of claim 13 wherein the polyvinyl alcohol has a molecular weight
of about 124k to about 180k daltons.
- 10 17. The method of claim 13 wherein the solution of polyvinyl alcohol comprises
isopropanol.
18. The method of claim 13 wherein the step of drying the slider further
15 comprises baking at a first temperature followed by baking at a second
temperature where the second temperature is higher than the first temperature.
19. The method of claim 13 wherein the second solvent comprises hot n-methyl-
2-pyrrolidone.
- 20 20. The method of claim 13 wherein the second solvent comprises dimethylpropyl
urea.
21. The method of claim 13 wherein the second solvent comprises boiling water.
- 25